

KUSASA SURE SKIM (CEMENT BASED)



GENERAL DATA

Description:	Kusasa Sure Skim is a grey cement based ready mixed skimming compound. The product comprises of binder compositions using rapid hardening cement, dolomite lime and redispersable acrylics that ensure the product is fully waterproofed with sufficient compressive strengths.
Recommended Use	Sure Skim is applied onto plastered surfaces, cement fibre boards / weather boards at a bed depth of 2-6mm (average). In isolated areas Sure Skim may be applied up to a maximum of 15mm. When using Sure Skim on cement fibre/weather board it is advisable to use to apply Kusasa Plaster Grip on the surfaces before Sure Skim is applied to aide adhesion quality on the board.

TECHNICAL DATA

Bulk Density:	1.5
Volume Solids:	Powder composition
Mixing Instructions:	Mix Kusasa Sure Skim at a rate of 20kg Sure Skim to 5-6lt of water. Water ratio dependant on ambient and application conditions that will vary from site to site.
Drying Time (hours):	Once mixed allow to thicken for 10 minutes and stir before use. 12 hours at a bed thickness of up to 6mm.
Colours:	Grey

APPLICATION DATA

Application Method:	Pack Kusasa Sure Skim onto the substrate using a steel trowel at a bed depth of 2-6mm. Once packed at a thickness of 2-6mm allow the product to stiffen and thereafter level the surface. Once hardened skim surface to a smooth finish.
Mixing Ratio:	5-6kg water to 20kg Kusasa Sure Skim
Pot Life:	30 minutes

RECOMMENDED SYSTEM

Primer:	1 coat Kusasa Solvent Based Sealer or Kusasa Plaster Primer or Kusasa Twin Pack Polyurethane / Epoxy Sealer
Finishing Coats:	2 coats Kusasa Acrylic/Mid or Low Sheen, Kusasa Polyurethane Enamel, Kusasa Gloss Enamel or Kusasa Twin pack Polyurethane/Epoxy (High water exposure)

MISCELLANEOUS

Flash Point:	Powder based
Shelf Life:	3 months in original sealed bags stored under correct storage conditions
Pack Sizes:	20kg

Note: We intend this publication to inform you about current practice without warranty. Information on the use of our products must be tested to local conditions before general application.

Telephone +27 (0) 31 464 8178, Facsimile +27 (0) 31 464 8179

E-mail info@kusasapaints.co.za