

DATA SHEETS

DECORATIVE COATINGS/TECHNICAL DATA SHEET

KUSASA UNIVERSAL UNDERCOAT



GENERAL DATA

Description:	A premium quality synthetic alkyd based undercoat or intermediate paint. The paint system gives maximum enamel holdout with good opacity. The paint must be overcoated with a topcoat.
Recommended Use	General purpose undercoat for use on all interior & exterior applications of wood, masonry, asbestos & metal.

TECHNICAL DATA

Specific Gravity:	1.28
Volume Solids:	65% (+/- 1%)
Opacity:	Good
Theoretical Spreading Rate:	Approximately 8-10 m ² / litre
Recommended DFT:	30-40 microns (1 coat)
Resin Type	Medium Alkyd Oil
Drying Time:	The temperature, humidity, air movement and film thickness will affect the drying time.
Touch Dry (hours):	4 hours
Dry to Recoat Time (hours):	12 hours
Hard Dry (Days):	7
Colours:	White & Black

APPLICATION DATA

Application Method:	Brush, Roller or Spray application.
Thinning (volume):	10-15% dilution depending on application method
Thinner / Cleaner:	Turps
Mixing Ratio:	N/A
Pot Life:	N/A

RECOMMENDED SYSTEM

Primer:	Kusasa Alkyd Undercoat - 1 coat
Finishing:	Kusasa Alkyd Enamel 1-2 coats Kusasa Acrylic Sheens 1-2 coats

MISCELLANEOUS

Flash Point:	Solvent based
Shelf Life:	12 months in original sealed containers under correct storage conditions

Note: We intend this publication to inform you about current practice without warranty. Information on the use of our products must be tested to local conditions before application.

Telephone +27 (0) 31 464 8178, Facsimile +27 (0) 31 464 8179, E-mail info@kusasapaints.co.za