

DATA SHEETS

DECORATIVE COATINGS/TECHNICAL DATA SHEET

KUSASA ZINC PHOSPHATE PRIMER



GENERAL DATA

Description:

A premium quality synthetic short oil alkyd based anti-corrosive primer pigmentated with Zinc Phosphate. The paint has good corrosion resistance, adhesion & fleexibility. Anti-corrosive primer for ferrous metals (Rust inhibitor)

Recommended Use

TECHNICAL DATA

Specific Gravity:	1.3
Volume Solids:	60% (+/- 1%)
Resin Solids	20%
Theoretical Spreading Rate:	Approximatly 8-10 m ² / litre
Recommended DFT:	30-40 microns (1 coat)
Resine Type:	Short Alkyd Oil
Drying Time:	The temperature, humidity, air movement and film thickness will affect the drying time.
Touch Dry (hours):	2 Hours
Dry to Recoat Time (hours):	4-6 hours
Hard Dry (Days):	24-48 hours
Colours:	Grey

APPLICATION DATA

Application Method:	Brush, Roller or Spray application.
Thinning (volume):	10-15% dilution depending on application method
Thinner / Cleaner:	Turps / thinners
Mixing Ratio:	N/A
Pot Life:	N/A

RECOMMENDED SYSTEM

Primer:	Kusasa Zinc Phosphate - 1 coat Kusasa Universal Undercoat - 1 coat
Finishing:	Kusasa Alkyd Enamel 1-2 coats

MISCELLANEOUS

Flash Point:	Solvent based
Shelf Life:	12 months in original sealed containers under correct storage conditions

Note: We intend this publication to inform you about current practice without warrenty. Information on the use of our products must be tested to local conditions before application.

Telephone +27 (0) 31 464 8178, Facsimile +27 (0) 31 464 8179, E-mail info@kusasapaints.co.za